



MATERIAL SPECIFICATION SHEET



Reclaimed Water High Density Polyethylene Tubing and Pipe

SCOPE:

This material specification designates the requirements for CB Supplies Ltd. Reclaimed Water HDPE, PE4710 cold water service tubing products. All Reclaimed Water CTS dimension tubing and IPS-ID dimension piping products meet the respective requirements of CSA B137.1, ASTM D2737 and ASTM D2239.

MATERIALS:

All Reclaimed Water tubing products are manufactured from PE4710 high density polyethylene resin. The inner layer contains a minimum of 2% carbon black ultraviolet light protection to meet the cell classification 445574C per ASTM D 3350. The outer purple layer contains pigments and ultraviolet stabilizers to meet the cell classification of 445574E per ASTM D 3350. Since both layers are UV protected, Reclaimed Water tubing and pipe can be stored outdoors in direct sunlight for up to 5 years with no change to its pressure rating or expected in-service performance.

MARKING & CERTIFICATION:

All Reclaimed Water tubing and piping products are marked with the name CB Supplies Ltd. as the manufacturer, Reclaimed Water, nominal size, design pressure and temperature ratings, relevant CSA and ASTM standard numbers, manufacturing date and production code.

RECOMMENDED USES:

Reclaimed Water tubing and pipe are intended and recommended for use in cold reclaimed water service systems and is not approved for potable water service. Design pressure / temperature rating @ 73.4°F (23°C) are 200 psi (1.38 Mpa) for SDR-9 tubing and SDR-7 pipe. For uses not listed here, consult with your CB Supplies Ltd. representative.

HANDLING & INSTALLATION:

Reclaimed Water high density polyethylene pipe and tubing products are tough yet flexible. However, they are softer than metals and may be damaged by abrasion or by objects with a cutting edge. Reclaimed Water tubing and pipe can be stored outdoors for up to 5 years before installation into a sunlight-shielded application with no change to the expected in-service performance. Reclaimed Water tubing and pipe may also be installed outdoors where it will be exposed to direct sunlight for up to 5 years. For pipe that is installed or remains outdoors after that limit, CB Supplies Ltd. expresses no in-service performance expectations. Do not drag or roll Reclaimed Water tubing or pipe coils across rocks or rough ground. Installation practices for Reclaimed Water tubing and pipe in trenched applications should comply with guidelines prepared by the Plastics Pipe Institute, American Water Works Association, Plastic Pipe and Fittings Association, and the manufacturer.

MATERIAL PROPERTIES:

MATERIAL PROPERTIES:

Property	ASTM Test Method	English Units	SI Units
Specific Gravity (Natural)	D792		0.951
Density (Black)	D4883		0.955 g/cc
Melt Index	D1238 (1)		8.5 g/10min
Tensile Strength (Yield)	D638 (2)	3600 psi	24.8 MPa
Tensile Elongation (Break)	D638 (2)	740%	740%
Flexural Modulus	D790B (2/3)	150000 psi	1034 MPa
Slow Crack Growth PENT	F1473	>5000 hr	> 5000hr
Notched Izod Impact	D256A (4)	9.10 ft-lb /in	0.48 kJ/m
Brittleness Temperature	D746A	<-103°F	<-75°C
Carbon Black Concentration	D1603	2.30%	2.30%
Cell Classification	D3350	445574C	445574C

1. 190°C/21600g 2. Condition C 3. Method 1,3 point load 4. 73°F

Reclaimed Water High Density Polyethylene Tubing and Pipe

CB Supplies Ltd. Reclaimed Water service tubing and pipe provides both simple identification of reclaimed water lines with its purple skin and long term UV resistance with its black inner core. CB Supplies Ltd. Reclaimed Water tubing (CTS) is manufactured in accordance with ASTM D2737 and CSA B137.1 and Reclaimed Water pipe (SIDR ID) is manufactured in accordance with ASTM D2239 and CSA B137.1. The Reclaimed Water tubing and pipe are indent printed for long-term identification requirements and incrementally marked for ease of installation. The exterior purple color is matched to the Pantone® 522 C color standard as required in some jurisdictions.

QUALITY ASSURANCE

When the product is marked with the CSA B137.1 and ASTM D 2737 or D 2239 designation, it affirms that the product was manufactured, inspected, sampled and tested in accordance with the specification and has been found to meet the specified requirements of the standards. Reclaimed Water service tubing and pipe are produced with state-of-the-art extrusion equipment to maintain consistency and accuracy.

200 PSI, CTS-OD, SDR-9, CSA B137.1 ASTM D2737, PE4710

Part Number	Nominal Size	Nominal O.D.	Min. Wall	Weight Per Foot
BEC4	3/4"	0.875	0.097	.103
BEC5	1"	1.125	0.125	.170
BEC6	1 1/4"	1.375	0.153	.255
BEC7	1 1/2"	1.625	0.181	.356
BEC8	2"	2.125	0.236	.608

200PSI, IPS-ID, SIDR-7, CSA B137.1 ASTM D2239, PE4710

Part Number	Nominal Size	Nominal I.D.	Avg. O.D.	Min. Wall	Weight Per Foot
BFH4	3/4"	0.824	1.060	.118	.159
BFH5	1"	1.049	1.349	.150	.253
BFH6	1 1/4"	1.380	1.774	.197	.434
BFH7	1 1/2"	1.610	2.070	.230	.591
BFH8	2"	2.067	2.657	.295	.973

PRESSURE DROP TABLE IPS-ID ALL SIDR'S

Expressed as PSI/FT Pressure Drop

GPM	Size					
	1/2"	3/4"	1"	1 1/4"	1 1/2"	2"
5	.085	.022	.007	.002	.001	.000
6	.119	.030	.009	.002	.001	.000
7	.158	.040	.012	.003	.002	.000
8	.202	.051	.016	.004	.002	.001
9	.251	.064	.020	.005	.003	.001
10	.306	.078	.024	.006	.006	.001
15		.165	.051	.013	.011	.002
20		.281	.087	.023	.016	.003
25			.131	.035	.023	.005
30			.184	.048	.030	.007
35				.064	.039	.009
40				.082	.048	.012
45				.103	.059	.014
50				.125	.070	.017
55				.149	.083	.021
60					.096	.024
65					.110	.028
70					.125	.033
75						.037
80						.042
90						.052
100						.063
110						.075
120						.088
125						.095

EXAMPLE: To calculate the pressure drop of a 3/4" line, 40 ft. long, with an 8 gpm flow rate, calculate .051 psi x 40 ft. = 2.04 psi pressure drop.

NOTE: Maximum flow for each size based on 12 FPS velocity.



CB SUPPLIES LTD.
www.cbsupplies.ca

PHONE: 1.800.665.1851
EMAIL: sales@cbsupplies.ca

3325 190th Street
Surrey, BC, Canada
V3Z 1A7